

approx. 84° Shore A
Recommended pretension 3...6 %

Crown Top PU 80 A orange smooth (14,3 x 6,3 mm)



Order No.	Profile dimension mm	Cross Section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley Ø		Fmax/belt (Standard)*	
				ft	(m)	mm	inch	kg	lbs
FBTJ143X630G	14,3 x 6,3	0,58	7,0	100	30,48	80	3,1	13,9	30,6

* = coefficient of friction μ :0,5

Coefficient of friction μ : Steel: approx. 0,65 | PE: approx. 0,35 | HDPE: approx. 0,30 | FDA/EC/USDA compliant



approx. 84° Shore A
Recommended pretension 3...6 %


PU 80 A T-Profile half-round orange smooth



Order No.	Profile dimension mm	Cross Section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley Ø		Fmax/belt (Standard)*	
				m	ft	mm	inch	kg	lbs
FBTJ192x550G	19,2 x 5,5	0,65	7,8	30	98,4	40	1,6	15,6	34,3

* = coefficient of friction μ :0,5

Coefficient of friction μ : Steel: approx. 0,65 | PE: approx. 0,35 | HDPE: approx. 0,30 | FDA/EC/USDA compliant



approx. 88° Shore A
Recommended pretension 3...6 %


T-Profile PU 85 A ultramarine blue smooth (9,5 x 3,5 mm)



Order No.	Profile dimension mm	Cross Section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley Ø		Fmax/belt (Standard)*	
				m	ft	mm	inch	kg	lbs
FBTK95X35L	9,5 x 3,5	0,20	2,4	50	164	50	2,0	5,2	11,4

* = coefficient of friction μ :0,5

Coefficient of friction μ : Steel: approx. 0,65 | PE: approx. 0,35 | HDPE: approx. 0,30 | FDA/EC/USDA compliant



approx. 88° Shore A
Recommended pretension 3...6 %

T-Profile PU 85 A for packaging machines (25 x 5 mm)

Order No.	Profile dimension mm	Cross Section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley Ø		Fmax/belt (Standard)*	
				m	ft	mm	inch	kg	lbs
FBTK25X5GW01	25 x 5	0,58	7,0	50	164	50	2,0	16,0	35,2

* = coefficient of friction μ :0,5

Coefficient of friction μ : Steel: approx. 0,60 | PE: approx. 0,35 | HDPE: approx. 0,30